



Inchcape Testing Services

Labtest

Labtest U.S.A. Inc.
101 West 51st Street
New York, NY 10001
Telephone (212) 866-7000
Fax (212) 867-2506

TEST REPORT

DISPLAY PRODUCTS, INC.
800 FABRIC XPRESS WAY
DALLAS, TX 75234

REPORT NO. 90073

June 7, 1995

IDENTIFICATION SUBMITTED BY CLIENT

Style FR66 PHEL-TEX 100% Polyester

FIRE RESISTANCE NFPA 701 - Small Scale

EVALUATION OF TEST RESULTS

The fabric submitted for testing **DOES** pass the flame resistance requirements when tested, after five commercial launderings, in accordance with procedures outlined in Chapter 8 of the National Fire Protection Association Standard 701.

IF YOU NEED ASSISTANCE INTERPRETING THESE TEST RESULTS
OR IF YOU HAVE ANY QUESTIONS, PLEASE FEEL FREE TO CALL:
ALMA BURROWES OR FLORENCE SLATER.

Test
Reference
90073
GP



LABTEST U.S.A., INC.

Alma Burrowes
Alma Burrowes
Director of Customer Service

-continued-

SUBJECT TO TERMS AND CONDITIONS ON BACK



TEST REPORT

PAGE 2

REPORT NO. 90073

June 7, 1995

IDENTIFICATION SUBMITTED BY CLIENT

Style FR66 PHIL-TEX 100% Polyester

TEST RESULTS

COMMERCIAL LAUNDERING PROCEDURE: AATCC 96 IVA
STATE OF SAMPLE: AFTER FIVE COMMERCIAL LAUNDERINGS
END USE: DRAPERY

WARP			FILLING		
AFTERFLAME (SECONDS)	CHAR LENGTH (INCHES)	BURNING OF DRIPPINGS	AFTERFLAME (SECONDS)	CHAR LENGTH (INCHES)	BURNING OF DRIPPINGS
--	4.6	NONE	--	3.8	NONE
--	4.2	NONE	--	4.1	NONE
--	4.4	NONE	--	4.7	NONE
--	4.5	NONE	--	3.9	NONE
--	3.9	NONE	--	4.3	NONE

Average Char Length for Ten Specimens: 4.2 Inches

REQUIREMENTS

Afterflame** Two seconds (Maximum) for any one specimen.
Length of Char* Based on the fabric weight of 6.5 Oz./Yd².
6.5 Inch average for ten specimens (Maximum).
7.5 Inch for any one specimen (Maximum).

Burning of Drippings Residues which break or drip from any test specimen shall not continue to flame after reaching the floor of the test chamber.**

****EXCEPT FOR FABRIC WEIGHING LESS THAN 10 OZS/YD² WITH END USE SPECIFIED AS DRAPERIES OR CURTAINS. AFTERFLAME DOES NOT APPLY
BURNING OF DRIPPINGS: 2 SECONDS MAXIMUM.**

<u>*WEIGHT OF FABRIC BEING TESTED</u>	<u>MAXIMUM AVERAGE CHAR LENGTH FOR TEN SPECIMENS</u>	<u>MAXIMUM CHAR LENGTH FOR ANY ONE SPECIMEN</u>
Over 10 Oz./Yd ²	3.5 Inches	4.5 Inches
6.1 - 10.0 Oz./Yd ²	4.5 inches	5.5 Inches
6.0 Oz./Yd ² or Less Draperies & Curtains	5.5 Inches	6.5 Inches
under 10 Ozs./Yd ² .	6.5 Inches	7.5 Inches

SUBJECT TO TERMS AND CONDITIONS ON BACK